

6980 Sierra Center Parkway, Suite 90  
Reno, NV 89511

March 24, 2010  
File: 1009

Mr. Chris Benna  
**RILITE AGGREGATES**  
3025 Mill Street  
Reno, NV 89502

**RE: Rilite Pit - 3/8-Inch Aggregate**

Dear Mr. Benna:

Per your request, we have performed aggregate quality testing on the sample of Rilite Pit 3/8-inch aggregate received by our laboratory on February 26<sup>th</sup>. Quality tests in comparison with ASTM C33 were performed for informational purposes. Test results in comparison with ASTM C330 specifications are as follows:

Sieve Size Analysis (ASTM C136/C117)		
U.S. Standard Sieve Size	Percent by Weight Passing	
	Rilite Pit	3/8-Inch Aggregate (9.5 mm to 2.36 mm) ASTM C330 Specifications
1/2 Inch	100	100
3/8 Inch	99	80 - 100
No. 4	39	5 - 40
No. 8	6	0 - 20
No. 16	5	0 - 10
No. 30	4	-
No. 200	1.4	0 - 10

Clay Lumps and Friable Particles (ASTM C142)	
Percent Total Sample	ASTM C330 Specification
0.2%	2.0% Maximum

Aggregate Unit Weight (ASTM C29)		
		ASTM C330 Specification
Dry Rodded Unit Weight	79.1 PCF	-
Dry Loose Unit Weight	71.5 PCF*	55 PCF Maximum

\*does not meet specification



Mr. Chris Benna  
**RILITE AGGREGATES**  
March 24, 2010  
Page 2

Specific Gravity and Absorption (ASTM C127)	
Bulk Specific Gravity (SSD Basis)	2.24
Absorption	4.9%

**Informational Testing:**

Los Angeles Abrasion (ASTM C131)	
Percentage Loss After 500 Revolutions 3/8-Inch Aggregate (Grading C)	ASTM C33 Specifications
49.8%	50% Maximum

Sodium Sulfate Soundness (ASTM C88)	
Weighted Percentage Loss	ASTM C33 Specification
9.1%	10% Maximum

Lightweight Pieces (ASTM C123)	
Percent of Total Sample	ASTM C33 Specification
0.2%	0.5% Maximum

We appreciate this opportunity to provide our laboratory testing services. If you have any questions or require further information, please do not hesitate to contact us.

Sincerely,

**CONSTRUCTION MATERIALS ENGINEERS, INC.**

Steven L. Vineis  
Laboratory Manager  
[svineis@cme-corp.com](mailto:svineis@cme-corp.com)  
Direct: 775-737-7568  
Direct Fax: 775-737-7605  
Mobile: 775-772-9921

Jon A. Del Santo, P.E.  
Project Manager  
RE Number 17094  
Expiration Date 12-31-10  
[jdelsanto@cme-corp.com](mailto:jdelsanto@cme-corp.com)  
Direct: 775-737-7564  
Direct Fax: 775-737-7602  
Mobile: 775-846-4399



SLV:JAD:jwl

v:\active\1009\2010\38\_inch\_agg\_03-24-10.doc

